

EXCURSION TEMPERATURE CAPABILITY			
Fluorelastomer (Viton®)		EPDM	
Temp. (°F)	Time (hrs)	Temp. (°F)	Time (hrs)
700	0.5	475	0.5
650	4	450	2
600	48	425	6
550	240	400	24
500	1,000	375	70
450	3,000	350	150
400	Continuous	325	300
		300	Continuous