

MATERIAL TEMPERATURE DATA

HJ 400 V Fluorelastomer (Viton®)		HJ 300 E EPDM	
Temp. (°F)	Time (hrs)	Temp. (°F)	Time (hrs)
700	0.5	475	0.5
650	4	450	2
600	48	425	6
550	240	400	24
500	1,000	375	70
450	3,000	350	150
400	Continuous	325 300	300 Continuous

MODEL	TEMPERATURE RATING
HJ 500 T	550 F
HJ 500 C	500 F
HJ 600 C – (E, T or V)	600 F
HJ 800 C – (T or V)	800 F
HJ 1000 C – (T or V)	1000 F
HJ 1200 C – (T)	1200 F